

## **Ink composition comprising siloxane surfactant and metal conductivity salt**

### ***Field of the Invention***

This invention relates to an ink composition, in particular an ink composition for use in continuous inkjet printing.

### ***Background to the Invention***

EP 1 879 969 is concerned with ingestible ink compositions for use in continuous inkjet printing directly onto foodstuffs and pharmaceuticals. These ink compositions comprise a liquid carrier, a colourant, a siloxane surfactant and, where these components would not provide sufficient electrical conductivity for continuous inkjet printing, a metal conductivity salt.

The siloxane surfactant is present in an amount of 0.1% by weight of the ink compositions of EP 1 879 969 and is stated to be for the purpose of modifying and regulating the surface tensions of the ink compositions.

EP 1 879 969 does not mention using the ingestible ink compositions to print on low surface energy substrates such as polypropylene (PP) and high- and low-density polyethylene (HDPE and LDPE), but, given the siloxane surfactant and conductivity salt content of these ink compositions, a person skilled in the art of ink formulation would expect the adhesion of these ink compositions to such low surface energy substrates to be poor.

It is an object of the present invention to provide an ink composition for continuous inkjet printing that has good adhesion to low surface energy substrates.

It is an alternative or additional object of the present invention to provide a commercially useful alternative to known ink compositions.

### ***Summary of the Invention***

The present invention provides an ink composition, in particular an ink composition for use in continuous inkjet printing, having a siloxane surfactant and a metal conductivity salt, which ink composition is suitable for producing printed images with good adhesion to low surface energy substrates, in particular, low energy substrates such as polypropylene, LDPE and HDPE.

Accordingly, in a first aspect, the present invention provides an ink composition comprising a liquid carrier, a colourant, a siloxane surfactant and a metal conductivity salt, wherein the

siloxane surfactant is present in an amount of at least 0.3% by weight of the ink composition and the siloxane surfactant comprises a polyether modified siloxane surfactant, ~~and wherein the metal conductivity salt is selected from the group consisting of lithium nitrate, potassium hexafluorophosphate, potassium thiocyanate, sodium thiocyanate, sodium iodide and potassium iodide, and wherein the colourant comprises a carbon black.~~

The combination in an ink composition of a siloxane surfactant present in an amount of at least 0.3% by weight of the ink composition and a metal conductivity salt surprisingly allows printed images to be produced on low surface energy substrates, which images have good adhesion to such substrates. This is contrary to the expectation that the adhesion to low surface energy substrates of an ink composition containing a siloxane surfactant and a conductivity salt would be poor.

In a second aspect the present invention provides an ink cartridge containing an ink composition of the first aspect.

In a third aspect the present invention provides a printing method comprising the steps of depositing an ink composition of the first aspect onto a substrate, and permitting at least partial evaporation of at least a component of the liquid carrier.

In some embodiments of the printing method of the third aspect, the step of depositing the ink composition onto the substrate comprises ejecting droplets of the ink composition from an inkjet print head onto the substrate.

In a fourth aspect the present invention provides an article marked with a printed deposit using the method of the third aspect.

In this way the invention provides an ink composition for producing a printed deposit and a printed deposit, which printed deposit has good adhesion to low surface energy substrates.

The ink composition is compatible with the components of an inkjet printer, and more particularly a continuous inkjet printer. The ink composition is suitable for application directly onto products and/or product packaging to achieve durable printed images.

These and other aspects and embodiments of the invention are described in further detail below.

### ***Summary of the Figure***

Figure 1 is a set of four pairs of digital microscope photographs of test images:

- 1-NS was printed using an ink otherwise in accordance with the invention but without the siloxane surfactant;
- 1 was printed using an ink in accordance with the invention. This is the same ink as in 1-NS except in this case the ink has the siloxane surfactant;
- C1-NS was printed using a comparative ink using a non-metal conductivity salt instead of the metal conductivity salt and without the siloxane surfactant; and
- C1 was printed using the comparative ink with a siloxane surfactant. This is the same ink as in C1-NS except in this case the ink has the siloxane surfactant.

The left hand one of each pair of photographs (A) being taken before, and the right hand one (B) after, a tape removal adhesion test on HDPE.

### ***Detailed Description of the Invention***

The invention provides an ink composition including a liquid carrier, a colourant, a siloxane surfactant and a metal conductivity salt, wherein the siloxane surfactant is present in an amount of at least 0.3% by weight of the ink composition and the siloxane surfactant comprises a polyether modified siloxane surfactant, ~~and wherein the metal conductivity salt is selected from the group consisting of lithium nitrate, potassium hexafluorophosphate, potassium thiocyanate, sodium thiocyanate, sodium iodide and potassium iodide, and wherein the colourant comprises a carbon black.~~ The liquid carrier may be in the form of an organic solvent.

The presence of the metal conductivity salt enables low conductivity colourants, such as non-ionic dyes and pigment dispersions, to be used in the ink compositions of the invention.

Low conductivity in this context means that the colourant alone does not provide the electrical conductivity required for continuous inkjet printing. That is to say, where the colourant of the ink composition of the invention is a low conductivity colourant, in the absence of the metal conductivity salt, the ink composition of the invention would have insufficient electrical conductivity for use in continuous inkjet printing.

Preferably the ink composition described herein has a viscosity of about 0.5 to 8 mPa.s, more preferably from 1 to 6.5 mPa.s and even more preferably from 2 to 5.5 mPa.s at 25°C. Preferably the ink composition described herein has a viscosity of less than 7 mPa.s, more preferably less than 5.5 mPa.s at 25°C. Preferably the ink composition described herein has a viscosity of greater than 0.5 mPa.s, more preferably greater than 1 mPa.s, even more preferably greater than 3 mPa.s at 25°C. The viscosity of the ink composition may be in a range with the upper and lower limits selected from the amounts described above. The

viscosity of the ink composition may be measured using a viscometer such as a Brookfield DV-II+ viscometer.

Preferably the ink composition as described herein has a static surface tension of from 20 to 50 mN/m, more preferably from 20 to 40 mN/m at 25°C, most preferably from 20 to 30mN/m. The static surface tension of the composition may be measured using equipment such as a du Nouy ring tensiometer or using the pendant drop method on a KSV Cam 200 optical tensiometer. The static surface tension of the ink composition may alternatively be measured using a bubble pressure tensiometer, such as a SITA pro line t15.

### *Colourant*

The ink composition and the printed deposit comprise a colourant. ~~The colourant comprises a carbon black. The colourant is not particularly limited and any suitable colourant known in the art may be used.~~

In some embodiments, the colourant may be a low conductivity colourant. Where the colourant is a low conductivity colourant, for example a non-ionic dye or a pigment dispersion, the electrical conductivity of the ink composition in the absence of the metal conductivity salt is less than 300  $\mu\text{S}/\text{cm}$ , and preferably less than 200  $\mu\text{S}/\text{cm}$ , at 25° C.

The electrical conductivity of the ink composition in the absence of the metal conductivity salt may be measured using an EDT Series 3 BA 380 conductivity meter using an EDT E8070 Polymer Conductivity Cell probe, with the sample warmed by a water bath at a temperature of 25 °C.

Where the colourant is a low conductivity colourant, in the absence of a metal conductivity salt the ink composition may be non-conductive because the low conductivity colourant is non-conductive. For example, the low conductivity colourant may be non-ionic (i.e. completely uncharged).

In some embodiments, the colourant is a non-ionic colourant, for example a non-ionic dye or a pigment. For example, it may be a completely uncharged dye such as Solvent Blue 104. Preferably the colourant is a pigment. The pigment may be in the form of a dispersion in the composition. The pigment may be an inorganic or an organic pigment.

The term 'non-ionic' as used herein refers to substances that are not ions and do not dissociate into ions in solution. That is, the term 'non-ionic' refers to substances which are not salts and contain no formal charge.



Where the colourant is a low conductivity colourant, in the absence of a metal conductivity salt the ink composition may have a low level of conductivity because the low conductivity colourant is an ionic complex with low dissociation in the liquid carrier. Low dissociation in this context means that the electrical conductivity of the ink composition in the absence of the metal conductivity salt is less than 300  $\mu\text{S}/\text{cm}$ , or preferably less than 200  $\mu\text{S}/\text{cm}$ , at 25° C.

In some embodiments, the colourant is a pigment in the form of an ionic complex with low or no dissociation in the liquid carrier. For example, it may be Pigment Blue 15:2, which is an ionic complex with low or no dissociation in most liquid carriers.

In other embodiments, the colourant is an ionic dye with good dissociation in the liquid carrier, but the colourant is present in a sufficiently low concentration that, in the absence of a metal conductivity salt, the electrical conductivity of the ink composition is less than 400  $\mu\text{S}/\text{cm}$ , preferably less than 300  $\mu\text{S}/\text{cm}$ , and more preferably still less than 200  $\mu\text{S}/\text{cm}$ .

It will be appreciated that a dispersion of a conductive pigment, such as carbon black, may constitute a low conductivity colourant if a dispersant and/or solvent forming part of the dispersion hinders electrical contact between the particles of the pigment.

Preferably, an ink composition comprising a low conductivity colourant has a conductivity in the absence of the metal conductivity salt of less than 400  $\mu\text{S}/\text{cm}$  at any concentration. More preferably, such an ink composition has a conductivity in the absence of the metal conductivity salt of less than 300  $\mu\text{S}/\text{cm}$ , for example, less than 200  $\mu\text{S}/\text{cm}$  and most preferably less than 100  $\mu\text{S}/\text{cm}$ .

In some cases, the colourant is present in the ink composition at between 1 to 25 wt % based on total weight of the ink composition, more preferably 1.3 to 15 wt %, and most preferably 2 to 7 wt % based on total weight of the ink composition.

An ink composition where the colourant is a low conductivity colourant and without a metal conductivity salt has a conductivity of less than 400  $\mu\text{S}/\text{cm}$  when the colourant is present in these amounts. More preferably, the ink composition without the metal conductivity salt has a conductivity of less than 300  $\mu\text{S}/\text{cm}$ , for example, less than 200  $\mu\text{S}/\text{cm}$  and most preferably less than 100  $\mu\text{S}/\text{cm}$ .

Preferably, an ink composition where the colourant is a low conductivity colourant and without a metal conductivity salt has a conductivity of less than 400  $\mu\text{S}/\text{cm}$  when the colourant is present in the ink composition at around 3 wt % based on total weight of the ink composition. More preferably, the ink composition without the metal conductivity salt has a

conductivity of less than 300  $\mu\text{S}/\text{cm}$ , for example, less than 200  $\mu\text{S}/\text{cm}$  and most preferably less than 100  $\mu\text{S}/\text{cm}$ .

Preferably the colourant is a low conductivity pigment. The low conductivity pigment may be in the form of a dispersion in the composition. The low conductivity pigment may be an inorganic or an organic pigment.

Preferably, the colourant comprises a carbon black. The carbon black may be provided as a solid (e.g. powder or bead) or a dispersion formulation (e.g. a dispersion in a solvent).

In this way, the present invention provides a carbon-black ink with good adhesion properties that can be used in coding and marking applications for example on common food packaging materials.

Carbon black may be produced by the incomplete combustion of heavy petroleum products such as FCC tar, coal tar, ethylene cracking tar or by charring organic materials such as wood or bone. Carbon black may be a form of paracrystalline carbon that has a high surface-area-to-volume ratio. Carbon black may contain oxygen complexes (e.g. carboxylic, quinonic, lactonic, phenolic groups and others) absorbed onto the surface of the carbon. In some cases carbon black may be acid-oxidized by spraying acid onto the carbon during the manufacturing process to change the inherent surface chemistry. The amount of chemically-bonded oxygen on the surface area of the carbon black can be increased to enhance performance characteristics.

Many carbon black products are advertised as conductive. Indeed, carbon black is conductive as a dry material. Nevertheless, carbon black may constitute a low conductivity colourant as referred to herein if the carbon black does not provide sufficient conductivity to the ink composition for continuous inkjet printing.

It is proposed that the electrons in carbon black as a dry material are free to move between the particles of the carbon black and provide conductivity, but are not free to move between the particles when the carbon black is suspended in the liquid carrier.

Carbon blacks suitable for the ink composition of the invention include carbon blacks manufactured by Mitsubishi Chemical Corporation, for example, No. 2300, No. 900, MCF 88, No. 33, No. 40, No. 45, No.52, MA 7, MA 8, MA 100, and No. 2200 B; carbon blacks manufactured by Columbian Carbon Co., Ltd., for example, Raven® 5750, Raven® 5250, Raven® 5000, Raven® 3500, Raven® 1255, and Raven® 700; carbon blacks manufactured by Cabot® Corporation, for example, Regal® 250R, Regal® 400 R, Regal® 330 R, Regal® 660 R, Mogul® L, Monarch® 700, Monarch® 800, Monarch® 880, Monarch® 900, Monarch® 1000, Monarch® 1100, Monarch® 1300, and Monarch® 1400; carbon blacks

manufactured by Orion, for example, Printex® 45, Printex® 35, Printex® nature, Special Black 350, Special Black 535, Printex® 3, Printex® 30, Special Black 275; and carbon blacks manufactured by Degussa, for example, Color Black FW 1, Color Black FW 2, Color Black FW 2 V, Color Black FW 18, Color Black FW 200, Color Black S 150, Color Black S 160, Color Black S 170, Printex® 35, Printex® U, Printex® V, Printex® 140 U, Special Black 6, Special Black 5, Special Black 4A, and Special Black 4.

Suitable pigments for use in yellow ink compositions of the invention include C.I. Pigment Yellow 1, C.I. Pigment Yellow 2, C.I. Pigment Yellow 3, C.I. Pigment Yellow 12, C.I. Pigment Yellow 13, C.I. Pigment Yellow 14, C.I. Pigment Yellow 16, C.I. Pigment Yellow 17, C.I. Pigment Yellow 73, C.I. Pigment Yellow 74, C.I. Pigment Yellow 75, C.I. Pigment Yellow 83, C.I. Pigment Yellow 93, C.I. Pigment Yellow 95, C.I. Pigment Yellow 97, C.I. Pigment Yellow 98, C.I. Pigment Yellow 109, C.I. Pigment Yellow 110, C.I. Pigment Yellow 114, C.I. Pigment Yellow 128, C.I. Pigment Yellow 129, C.I. Pigment Yellow 138, C.I. Pigment Yellow 150, C.I. Pigment Yellow 151, C.I. Pigment Yellow 154, C.I. Pigment Yellow 155, C.I. Pigment Yellow 180, C.I. Pigment Yellow 185, and C.I. Pigment Yellow 139.

Suitable pigments for use in magenta ink compositions of the invention include C.I. Pigment Red 5, C.I. Pigment Red 7, C.I. Pigment Red 12, C.I. Pigment Red 48 (Ca), C.I. Pigment Red 48 8 (Mn), C.I. Pigment Red 57 (Ca), C.I. Pigment Red 57 : 1, C.I. Pigment Red 112, C.I. Pigment Red 122, C.I. Pigment Red 123, C.I. Pigment Red 168, C.I. Pigment Red 184, C.I. Pigment Red 202, C.I. Pigment Red 176, C.I. Pigment Red 254, C.I. Pigment Red 255, C.I. Pigment Red 272, C.I. Pigment Red 254, C.I. Pigment Orange 64, and C.I. Pigment Orange 73.

Suitable pigments for use in cyan ink compositions of the invention include C.I. Pigment Blue 1, C.I. Pigment Blue 2, C.I. Pigment Blue 3, C.I. Pigment Blue 15 : 3, C.I. Pigment Blue 15 : 34, C.I. Pigment Blue 16, C.I. Pigment Blue 22, C.I. Pigment Blue 60, C.I. Vat Blue 4, C.I. Vat Blue 60, C.I. Pigment Blue 15:2, C.I. Pigment Blue 15:4, C.I. Pigment Green 3, C.I. Pigment Violet 23 and C.I. Pigment Violet 37.

Preferably, the pigment is an organic pigment selected from C.I. Pigment Red 176, C.I. Pigment Red 254, C.I. Pigment Red 255, C.I. Pigment Red 272, C.I. Pigment Red 254, C.I. Pigment Orange 64, C.I. Pigment Orange 73, C.I. Pigment Yellow 83, C.I. Pigment Yellow 138, C.I. Pigment Yellow 139, C.I. Pigment Yellow 151, C.I. Pigment Yellow 154, C.I. Pigment Blue 15:2, C.I. Pigment Blue 15:3, C.I. Pigment Blue 15:4, C.I. Pigment Green 3, C.I. Pigment Violet 23 and C.I. Pigment Violet 37.

Low conductivity organic pigments may be selected from carbon black, polycyclic pigments (for example, phthalocyanine, perylene, perinone, anthraquinone, quinacridone, dioxazine, thioindigo, isoindolinone, and quinophthalone pigments) and azo-pigments.

Suitable dyes include Oil Black 860 (C.I. Solvent Black 3), Solvaperm® Blue 2B or other Solvent Blue 104 dyes, Orasol® Blue 855, Orasol® Blue 825 (C.I. Solvent Blue 67), Neptune® Blue 722 (C.I. Solvent Blue 4), Oil Blue 613 (C.I. Solvent Blue 5), Savinyl® Blue GLS (C.I. Solvent Blue 44), Valifast® Blue 2606 (C.I. Solvent Blue 70), Valifast® Blue 2620 (C.I. Solvent Blue 44), Millijet Black J10, C.I. Solvent Black 7, 27, 28, 29, 35, 48, 49, C.I. Solvent Blue 35, 38, 44, 45, 79, 98, 100, 129, C.I. Solvent Red 8, 49, 68, 89, 124, 160, 164, C.I. Solvent Yellow 83:1, 126, 146, 162, C.I. Solvent Green 5, C.I. Solvent Orange 97, C.I. Solvent Brown 20, 52, and C.I. Solvent Violet 9, of which Solvaperm® Blue 2B and Orasol® Blue 855 are preferred low conductivity dyes and C.I. Solvent Black 27 and 29 are preferred ionic dyes with good dissociation in common organic solvents.

Preferably the colourant is present in between 1 to 25 wt % based on total weight of the ink composition, more preferably 1.3 to 15 wt %, and most preferably 2 to 7 wt % based on total weight of the ink composition.

Preferably, the colourant is present in less than 25 wt % based on total weight of the ink composition, more preferably less than 15 wt %, more preferably less than 6 wt% and even more preferably less than 4 wt %. Preferably, the colourant is present in greater than 1 wt % based on total weight of the ink composition, preferably greater than 1.3 wt %, and even more preferably greater than 2 wt %. The colourant may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

In this way the ink composition may have the desired opacity and colour.

#### *Metal Conductivity Salt*

The ink composition and the printed deposit comprise a metal conductivity salt.

The combination of a metal conductivity salt and a siloxane surfactant present in an amount of at least 0.3% by weight of the ink composition surprisingly results in an improvement to the generally poor adhesion to low surface energy substrates of printed images produced using ink compositions containing a siloxane surfactant and a metal conductivity salt. That is, the combination provides improved adhesion to low surface energy substrates. This reversal of the detrimental effect of the presence of a siloxane surfactant and a metal conductivity salt on adhesion is surprising, in particular given that the reversal is not observed when non-metal conductivity salts are used in an ink composition.

Salts are composed of related numbers of cations (positively charged ions) and anions (negatively charged ions) so that the product is electrically neutral (without a net charge). A metal conductivity salt is a salt in which the cation is a metal cation.

The metal conductivity salt is selected from lithium nitrate, potassium hexafluorophosphate, potassium thiocyanate, sodium thiocyanate, sodium iodide or potassium iodide. Preferably, the metal conductivity salt is potassium hexafluorophosphate and/or potassium iodide.

Preferably, the metal conductivity salt is present at 4.0 wt % or less based on total weight of the ink composition, more preferably 2.0 wt % or less and even more preferably 1.5 wt % or less. Preferably, the metal conductivity salt is present at 0.3 wt % or more based on total weight of the ink composition, preferably 0.5 wt % or more, and even more preferably 0.8 wt % or more. The metal conductivity salt may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above. For example, the metal conductivity salt is present at 0.3 to 4.0 wt % based on total weight of the ink composition.

Preferably, the metal conductivity salt is present in an amount that provides an ink composition with a conductivity of less than 2200  $\mu\text{S/cm}$ , more preferably less than 1900  $\mu\text{S/cm}$  and even more preferably less than 1500  $\mu\text{S/cm}$ . Preferably, the metal conductivity salt is present in an amount that provides an ink composition with a conductivity greater than 200  $\mu\text{S/cm}$ , preferably greater than 500  $\mu\text{S/cm}$ , preferably greater than 800  $\mu\text{S/cm}$ , and even more preferably greater than 1200  $\mu\text{S/cm}$ . The metal conductivity salt may be present in an amount to give a conductivity that is in a range with the upper and lower limits selected from the amounts described above. For example, the ink composition has a conductivity of from 500 to 2200  $\mu\text{S/cm}$ .

Conductivity may be measured using an EDT Series 3 BA 380 conductivity meter using an EDT E8070 Polymer Conductivity Cell probe, with the sample warmed by a water bath at a temperature of 25°C.

#### *Siloxane Surfactant*

The ink composition further comprises a siloxane surfactant present in an amount of at least 0.3% by weight of the ink composition.

A siloxane surfactant is a surfactant having a siloxane functional group (i.e. an Si—O—Si linkage).

The siloxane surfactant comprises a polyether modified siloxane surfactant.

Preferably, the siloxane surfactant is present in less than 4.0 wt % based on total weight of the ink composition. The siloxane surfactant is present in greater than 0.3 wt %, preferably greater than 0.5 wt %, preferably greater than 0.7 wt %, and even more preferably greater

than 0.9 wt %. Preferably, the siloxane surfactant is present at about 1.0 wt % based on the total weight of the ink composition. The siloxane surfactant may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

Preferably the siloxane surfactant has a viscosity of about 100 to 3000 mPa.s, more preferably from 500 to 2500 mPa.s, more preferably from 1000 to 2500 mPa.s, and even more preferably from 1500 to 2500 mPa.s at 25 °C. Preferably the siloxane surfactant has a viscosity of less than 3000 mPa.s, more preferably less than 2000 mPa.s at 25°C. Preferably the siloxane surfactant has a viscosity of greater than 100 mPa.s, more preferably greater than 500 mPa.s, more preferably greater than 1000 mPa.s, more preferably greater than 1500 mPa.s, even more preferably greater than 1700 mPa.s at 25°C. The viscosity of the siloxane surfactant may be in a range with the upper and lower limits selected from the amounts described above. The viscosity of the siloxane surfactant may be measured using a viscometer such as a Brookfield DV-II+ viscometer.

In some cases, a siloxane surfactant is obtained pre-diluted in a solvent. The viscosity of the siloxane surfactant may refer to the viscosity of the pre-diluted solution or to the siloxane surfactant before dilution. Preferably, the viscosity refers to the siloxane surfactant before dilution, i.e. the viscosity is the viscosity of the siloxane surfactant *per se*.

#### *Solvents*

The liquid carrier of the ink composition may comprise an organic solvent or a mixture of organic solvents. Any organic solvent or mixture which can dissolve the colorant is suitable. A solvent may be selected from ketones, alcohols, esters, glycols, glycol ethers, carbonates or a mixture thereof.

For example, an organic solvent may be selected from acetone, methyl ethyl ketone, methyl propyl ketone, methyl isobutyl ketone, cyclohexanone, ethanol, isopropanol, n-propanol, isobutanol, n-butanol, sec-butanol, methyl acetate, ethyl acetate, n-propyl acetate, isopropyl acetate, n-butyl acetate, isobutyl acetate, t-butyl acetate, n-amyl acetate, isoamyl acetate, isobutyl isobutyrate, ethylene glycol, propylene glycol, 1-methoxy-2-propanol and 1-methoxy-2-propyl acetate, dimethyl carbonate or a mixture thereof.

Preferably, an organic solvent may be selected from acetone, methyl ethyl ketone, ethanol, methyl acetate and ethyl acetate or a mixture thereof. In particular, a combination of methyl ethyl ketone with ethanol, ethanol with ethyl acetate and/or methyl acetate, ethanol with 1-methoxy-2-propanol or acetone with methyl acetate may be used.

Preferably, the organic solvent or mixture of organic solvents is present in the composition between 10 to 95 wt %, more preferably 40 to 90 wt %, and most preferably 70 to 90 wt % by weight based on total weight of the ink composition.

Preferably, the organic solvent or mixture of organic solvents is present in less than 95 wt % based on total weight of the ink composition, more preferably less than 90 wt % and even more preferably less than 85 wt %. Preferably, the solvent is present in greater than 10 wt % based on total weight of the ink composition, preferably greater than 40 wt %, and even more preferably greater than 70 wt %. The solvent may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

A preferred organic solvent for use is a ketone, such as methyl ethyl ketone. Preferably, the ketone, such as methyl ethyl ketone, is present from 10 to 90 wt %, more preferably 60 to 87 wt %, and most preferably 75 to 85 wt % based on total weight of the ink composition.

Preferably, the ketone, such as methyl ethyl ketone, is present in less than 90 wt % based on total weight of the ink composition, more preferably less than 87 wt % and even more preferably less than 85 wt %. Preferably, the ketone, such as methyl ethyl ketone, is present in greater than 10 wt % based on total weight of the ink composition, preferably greater than 60 wt %, and even more preferably greater than 75 wt %. The ketone may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

When the organic solvent is a mixture, the mixture preferably comprises a ketone with an alcohol such as a C<sub>1-6</sub> alkyl alcohol or an ester with an alcohol or a ketone with an ester. The alcohol may be a C<sub>1-6</sub> alkyl alcohol such as isopropanol or ethanol, preferably ethanol. The ester may be a C<sub>1-6</sub> alkyl C<sub>1-6</sub> alkanooate such as ethyl acetate or methyl acetate. The ketone may be a C<sub>1-6</sub> alkyl- a C<sub>1-6</sub> alkyl ketone, for example acetone or methyl ethyl ketone (MEK).

Preferred mixtures comprise methyl ethyl ketone and ethanol or isopropanol, such as ethanol. In this case, preferably methyl ethyl ketone, is present in less than 90 wt % based on total weight of the ink composition, more preferably less than 80 wt % and even more preferably less than 70 wt %. Preferably, methyl ethyl ketone, is present in greater than 10 wt % based on total weight of the ink composition, preferably greater than 45 wt %, and even more preferably greater than 55 wt %. In this case, preferably, the alcohol is present from 5 to 20 wt %, more preferably 10 to 15 wt %, based on total weight of the ink composition. Preferably, the alcohol is present in less than 20 wt % based on total weight of the ink composition, more preferably less than 15 wt %. Preferably, the alcohol is present in greater than 5 wt % based on total weight of the ink composition, preferably greater than 10 wt %.



The methyl ethyl ketone and alcohol may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

Preferred mixtures comprise acetone with methyl acetate and/or ethyl acetate, such as methyl acetate and ethyl acetate. In this case, preferably acetone, is present in less than 80 wt % based on total weight of the ink composition, more preferably less than 60 wt % and even more preferably less than 50 wt %. Preferably, acetone, is present in greater than 10 wt % based on total weight of the ink composition, preferably greater than 30 wt %, and even more preferably greater than 40 wt %. In this case, preferably, the ester(s) is present from 5 to 40 wt %, more preferably 10 to 30 wt %, based on total weight of the ink composition. Preferably, the ester(s) is present in less than 30 wt % based on total weight of the ink composition, more preferably less than 25 wt %. Preferably, the ester(s) is present in greater than 5 wt % based on total weight of the ink composition, preferably greater than 15 wt %. The acetone and ester(s) may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

Preferred mixtures comprise an alcohol, such as ethanol, with methyl acetate or ethyl acetate, such as ethyl acetate. In this case, preferably the alcohol, such as ethanol, is present in less than 70 wt % based on total weight of the ink composition, more preferably less than 50 wt % and even more preferably less than 40 wt %. Preferably, the alcohol, such as ethanol, is present in greater than 10 wt % based on total weight of the ink composition, preferably greater than 20 wt %, and even more preferably greater than 30 wt %. In this case, preferably, the ester is present from 10 to 70 wt %, more preferably 20 to 50 wt %, based on total weight of the ink composition. Preferably, the ester is present in less than 60 wt % based on total weight of the ink composition, more preferably less than 40 wt %. Preferably, the ester is present in greater than 20 wt % based on total weight of the ink composition, preferably greater than 30 wt %. The alcohol and ester may be present in an amount that is in a range with the upper and lower limits selected from the amounts described above.

Preferred mixtures comprise acetone with an alcohol such as ethanol. In this case, preferably acetone, is present in less than 80 wt % based on total weight of the ink composition, more preferably less than 60 wt % and even more preferably less than 50 wt %. Preferably, acetone, is present in greater than 10 wt % based on total weight of the ink composition, preferably greater than 30 wt %, and even more preferably greater than 40 wt %. In this case, preferably, the alcohol is present from 5 to 40 wt %, more preferably 10 to 30 wt %, based on total weight of the ink composition. Preferably, the alcohol is present in less than 30 wt % based on total weight of the ink composition, more preferably less than 25 wt %. Preferably, the alcohol is present in greater than 5 wt % based on total weight of the ink composition, preferably greater than 15 wt %. The acetone and alcohol may be present



in an amount that is in a range with the upper and lower limits selected from the amounts described above.

The ink composition is preferably a non-aqueous composition.

The ink composition may also contain water. For example, if present, water may be present at 10 wt % or less based on the total weight of the ink composition, and preferably water is present at 5 wt % or less.

In the printed deposit the liquid carrier or at least a component of the liquid carrier will have at least partially evaporated. In this case, it may be that no liquid carrier or only trace amounts of liquid carrier are present in the printed deposit.

#### *Binders*

A binder, such as a binder resin, may be present in the inkjet composition.

The binder comprises one or more polymers. The binder may be selected from any suitable binder, for example, suitable binders include polyamide resins, polyurethane resins, rosin ester resins, acrylic resins, polyvinyl butyral resins, polyesters, phenolic resins, vinyl resins, polystyrene/polyacrylate copolymers, cellulose ethers, cellulose nitrate resins, polymaleic anhydrides, acetal polymers, polystyrene/polybutadiene copolymers, polystyrene/polymethacrylate copolymers, sulfonated polyesters, aldehyde resins, polyhydroxystyrene resins and polyketone resins and mixtures of two or more thereof.

Preferably, the binder is selected from cellulosic resins, acrylic resins, vinyl resins, polyamides, polyesters, polyvinyl (e.g. polyvinyl butyral (PVB)), and polyurethanes. More preferably, the binder is a cellulosic resin. Even more preferably, the cellulosic resin is cellulose acetate butyrate.

Preferably, the binder has a molecular weight, such as a weight average molecular weight (Mw) between 500 and 50,000, more preferably between 1,500 and 50,000, more preferably between 10,000 and 50,000 and even more preferably between 15,000 and 50,000. Preferably, the binder has a molecular weight, such as a weight average molecular weight (Mw) of at least 500, more preferably at least 1,500, more preferably at least 10,000 and even more preferably at least 15,000. Preferably, the binder has a molecular weight, such as a weight average molecular weight (Mw) less than 50,000. The binder has a molecular weight, such as a weight average molecular weight (Mw) that is in a range with the upper and lower limits selected from the amounts described above.

In the ink compositions described below the cellulose binder resin CAB-551-0.1 is used. CAB-551-0.1 is shortened to CAB551 in the following description. In the ink compositions described below the binder Foralyn® 110 is used. Foralyn® 110 is also referred to as 'Foralyn®' in the following description.

### *Additives*

The ink composition and the printed deposit may contain additional components, such as those commonly used in the art.

For example, the ink composition and the printed deposit may further comprise one or more preservatives, humectants, additional surfactants, plasticizers, wetting agents, adhesion promotion additives, biocides and mixtures of two or more thereof.

### *Humectants*

Preferably, the ink composition and the printed deposit further comprise a humectant.

Suitable humectants include ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,4-cyclohexanedimethanol, 1,5-pentanediol, 1,6-hexanediol, 1,8-octanediol, 1,2-propanediol, 1,2-butanediol, 1,3-butanediol, 2,3-butanediol, diethylene glycol, triethylene glycol, tetraethylene glycol, polyethylene glycol, dipropylene glycol, polypropylene glycol, glycerol, 1,2,6-hexanetriol, sorbitol, 2-pyrrolidone, 2-propanediol, butyrolacetone, tetrahydrofurfuryl alcohol and 1,2,4-butanetriol and mixtures of two or more thereof. Preferably the humectant is selected from a group consisting of glycerol, tetrahydrofurfuryl alcohol, polypropylene glycol and mixtures of two or more thereof.

### *Preservatives*

Preferably, the ink composition and the printed deposit further comprise a preservative.

Suitable preservatives include sodium benzoate, benzoic acid, sorbic acid, potassium sorbate, calcium sorbate, calcium benzoate, methylparaben and mixtures of two or more thereof. The preferred preservative is sodium benzoate.

The ink composition may comprise up to 2% by weight of preservative based on the total weight of the composition. More preferably, the ink composition comprises up to 1% by weight of preservative based on the total weight of the composition.

### *Tackifier*

Preferably, the inkjet ink composition and the printed deposit further comprise a tackifier.

In some cases the tackifier may be a binder; preferably, when the tackifier is a binder it is used in combination with a co-binder. In some cases, the tackifier is a non-film forming polymer. In some cases, the tackifier may be used in combination with other polymers to produce the desired properties.

Suitable tackifiers include resins such as rosins, terpenes and modified terpenes, aliphatic, cycloaliphatic and aromatic resins, terpene phenolic resins and silicone or mineral oils. Preferably the tackifiers are a terpene phenolic resin and/or an ester of hydrogenated rosin. Most preferably the tackifier is a terpene phenolic resin.

The ink composition may comprise from 0.3 to 10 % by weight of tackifier based on the total weight of the composition. More preferably, the ink composition comprises from 1 to 5 % by weight of tackifier based on the total weight of the composition.

#### *Adhesion Promoter*

Preferably, the inkjet ink composition and the printed deposit further comprise an adhesion promoter.

An adhesion promoter is a substance which acts to promote adhesion of the ink composition to a substrate.

Suitable adhesion promoters are titanium phosphate complex, titanium acetylacetonate, triethanolamine zirconate, zirconium citrate, zirconium propanoate, organosilicon, polyketones binders, polyesters binders, or a ketone condensation resin.

Preferably the adhesion promoter is a titanium phosphate complex or a ketone condensation resin. More preferably, the adhesion promoter is a ketone condensation resin.

#### *Dispersant*

Preferably, the ink composition and the printed deposit further comprise a pigment dispersant. Suitable dispersants include ionic and non-ionic dispersants. Preferably the dispersant is an acrylic block co-copolymer.

#### *Types of Packaging*

Also described is a method for printing images on a substrate comprising directing a stream of droplets of any of the embodiments of the ink composition of the invention onto the

substrate and allowing the ink droplets to dry, thereby printing images on the substrate. Preferably, an inkjet printer such as a continuous inkjet printer is used in the method.

The ink composition of the present invention is particularly suitable for printing on non-porous substrates, in particular non-porous low surface energy substrates such as are typically used for food packaging.

Examples of such food packaging include aluminium or steel cans, and pots, retort pouches, and flexible films made from low density polyethylene (LDPE), high density polyethylene (HDPE), polypropylene (PP), PET, nylon or PVdC. Preferably, the substrate is a LDPE, HDPE or PP substrate.

#### *Methods and Uses*

The ink compositions are formulated by combining the components using methods known in the art.

The components of the ink composition may be combined by adding the components together and stirring using mechanical agitation. In some cases the components may be added in the following order: solvent, binder, surfactant, additional additives, colourant, dispersion and the conductivity salt.

Also described is a method for printing images on a substrate in a continuous inkjet printer comprising directing a stream of droplets of any of the embodiments of the ink composition to a substrate and allowing the ink droplets to dry, thereby printing images on a substrate. Any suitable substrate may be printed.

Examples of suitable substrates include porous substrates such as uncoated paper, semi-porous substrates such as aqueous coated paper, clay coated paper, silica coated paper, UV overcoated paper, polymer overcoated paper, and varnish overcoated paper, and non-porous substrates such as hard plastics, polymer films, polymer laminates, metals, metal foil laminates, glass, and ceramics. The paper substrates may be thin sheets of paper, rolls of paper, or cardboard. Plastics, laminates, metals, glass, and ceramic substrates may be in any suitable form such as in the form of bottles or containers, plates, rods, cylinders, etc.

Preferably, the ink composition as described herein is suitable for coding and marking, in particular for coding and marking on food packaging. It is particularly preferred that the ink composition is useful for printing on plastic or paper wrappers of food or beverage products, for example for printing the expiration date on such packaging.

Advantageously, using the compositions and methods described herein overcomes and/or mitigates at least some of the problems described above, providing an improved quality print.

The invention further provides a printed article comprising an article on which a printed deposit has been formed using the ink composition of the invention.

### *Definitions*

As used herein the term printed deposit refers to the ink composition after it has been printed onto a suitable substrate, and at least partially allowed to dry. That is, the ink composition of the present invention wherein at least some of the liquid carrier has evaporated.

An ink composition may be an inkjet ink composition suitable for use in inkjet printing. The ink composition is typically in the form of a liquid, and typically a solution.

The term C<sub>1-6</sub> alkyl alcohol refers to any solvent having at least one hydroxyl function group (-OH) and having between 1 and 6 carbon atoms.

A polymer is any substance having a repeat unit and includes: polysaccharides and their derivatives, for example cellulose and its derivatives; addition polymers such as acrylic resins or polyvinyl resins; condensation polymer, for example polyurethanes, polyamide and polyesters; and co-polymers wherein the repeat unit is formed of two or more different compounds, for example of styrene and maleic anhydride.

### *Extent of Disclosure*

“and/or” where used herein is to be taken as specific disclosure of each of the two specified features or components with or without the other. For example “A and/or B” is to be taken as specific disclosure of each of (i) A, (ii) B and (iii) A and B, just as if each were set out individually herein.

Certain aspects and embodiments of the invention will now be illustrated by way of example and with reference to the figure described above.

### *Examples*

The following non-limiting examples further illustrate the present invention.

Viscosity was measured using the Brookfield DV-E viscometer fitted with a UL adaptor. The viscosity was measured with the sample immersed in a water bath at a temperature of 25°C in a room with a pressure of 1.013 kPa and humidity of 70 %.

Conductivity was measured using an EDT Series 3 BA 380 conductivity meter using an EDT E8070 Polymer Conductivity Cell probe. The conductivity was measured with the sample warmed by a water bath at a temperature of 25°C.

#### *Printed Ink Properties*

Prior to printing, the inks were filtered through 1 µm filter paper.

Print samples were created using a Domino® Ax-Series print sample rig fitted with a 60 µm nozzle. Adhesion of the inks was assessed using a printed image in the form of a 9\*9 array of droplets printed onto HDPE, LDPE and PP substrates. The HDPE, LDPE and PP substrates were as follows:

Substrate	Specification	Supplier
HDPE	1.5mm HDPE 300 sheet, natural	Engineering and Design Plastics Ltd, Cambridge, UK
LDPE	1.5 mm sheet, natural	Engineering and Design Plastics Ltd, Cambridge, UK
Polypropylene	1.5 mm natural sheet	Engineering and Design Plastics Ltd, Cambridge, UK

The 60 µm nozzle was flushed with the main ink solvent prior to use each time. The substrates were cleaned with paper towels dampened with Ethanol (DEB 100) prior to printing.

#### *Tape Removal Adhesion Tests*

Tape removal adhesion tests were performed using both Scotch® grade 810 (19.05 mm wide) and ISO 2409 Adhesive Tape supplied by Elcometer adhesive tapes. Scotch® grade 810 (19.05 mm wide) is referred to as '810' tape and ISO 2409 is referred to as 'ISO' tape in the following description.

The tests were performed 24 h after printing. The tape removal adhesion tests were carried out at 20 to 25 °C with a relative humidity of 25 to 45%.

Around 10 cm of the tape to be tested was cut from the reel. The tape was applied to the printed image to cover the printed image completely, leaving a tail portion unattached to allow the tape to be removed. The tape was applied so that the tape did not crease or contain air bubbles. A pencil eraser was used to ensure that the tape was in uniform contact

with the substrate by pressing the eraser on the centre line of the tape and pressing outwards to each edge, working along the length of the adhered portion of the tape.

The tape was then removed by pulling the unattached tail portion of the tape in a swift motion that combined both a lifting and a pulling action whilst holding the substrate firmly in place. Each test was carried out in triplicate.

The adhesion performance was scored by comparing pairs of digital microscope photographs of the printed images taken before tape application and after tape removal using Matlab® software. Each such test was carried out in triplicate.

The Matlab® software is used as follows:

1. A digital photograph of the printed image is taken using a Celestron® Model 44302-b handheld digital microscope.
2. The digital photograph is transferred to a PC running the Matlab® software.
3. The Matlab® software finds a threshold value for the binarised digital photograph using Otsu's Method (i.e.  $\text{level} = \text{graythresh}(I)$ ).
4. The Matlab® software converts the digital photograph to black and white only, i.e., binarises the digital photograph, using the threshold value and filters out artefacts smaller than 10 pixels.
5. The Matlab® software calculates the sum of the areas of the remaining features in the filtered binarised digital photograph using the function `regionprops`.

This process is carried out for the printed image before the tape has been applied and after it has been removed. The sum of the areas of the remaining features after the tape has been removed is deducted from the sum of the areas of the remaining features before the tape was applied.

The percentage of ink removed is calculated as follows:

$$\text{Percentage ink removed} = \left[ \frac{(\text{sum of areas before tape applied} - \text{sum of areas after tape removed})}{\text{sum of areas before tape applied}} \right] \times 100.$$

### *Ink Compositions*

Two carbon black pigment dispersions were prepared for use as colourants.

The first dispersion, referred to below as Pigment Dispersion 01, was prepared as follows. 34 wt % of MEK was mixed with 36 wt % of BASF® EFKA® PX 4320 dispersant using mechanical agitation. Once homogeneous, 30 wt % of Cabot® Regal® 250R carbon black

pigment was added and mixed using a Dispermat® AE 01-M1-EX high shear mixer until homogeneous to create a pre-dispersion. The pre-dispersion was milled using an Eiger Torrance lab-scale beads attrition mill loaded 85% with 0.8 mm ceramic beads.

The second dispersion, referred to below as Pigment Dispersion 02, was prepared as follows. 40 wt % of ethyl acetate was mixed with 30 wt % of BASF® EFKA® PX 4320 dispersant using the Dispermat® AE 01-M1-EX high shear mixer. Once homogeneous, 30 wt % of Cabot® Regal® 250R carbon black pigment was added and mixed using the same high shear mixer until homogeneous to create a pre-dispersion. The pre-dispersion was milled using an Eiger Torrance beads attrition mill loaded 85% with 0.8 mm ceramic beads.

Inks were prepared by addition of the components in the following order with magnetic stirring: solvent, binder, surfactant, colourant and conductivity salt.

The complete inks were shaken on a lab shaker for 30 minutes prior to use.

Invention ink and comparative ink compositions were prepared with the formulations set out in Table 1 below. The amounts of the components are provided as wt % based on the total weight of the ink composition. The solvent is used to make up the balance of the ink composition in each case.

For each invention ink and comparative ink in Table 1 below, there is also a corresponding ink (labelled "NS") which does not contain the siloxane surfactant. For example, "Ink 1" is the same as "Ink 1-NS" except for the presence of the siloxane surfactant Tego Glide® 410.

12 05 23



Table 1 – Invention Ink and Comparative Ink Compositions

Ink	Salt used	Raw materials wt.%					Solvent used to make up the formulation to 100wt.%	Conductivity $\mu\text{S}/\text{cm}$
		Salt	CAB-551-0.01	Foralyn® 110	Tego Glide® 410	Pigment Dispersion 01		
1	KPF6	1.00	9.00	5.00	1.00	5.00	MEK	1326
1-NS	KPF6	0.98	9.00	5.00	0.00	5.00	MEK	1347
2	NaI	0.89	9.00	5.00	1.00	5.00	MEK	908
2-NS	NaI	0.80	9.00	5.00	0.00	5.00	MEK	990
3	KSCN	1.01	9.00	5.00	1.00	5.00	MEK	1070
3-NS	KSCN	1.03	9.00	5.00	0.00	5.00	MEK	1140
4	NaSCN	1.00	9.00	5.00	1.00	5.00	MEK	750
4-NS	NaSCN	0.99	9.00	5.00	0.00	5.00	MEK	810
Comp. 1	TBAPF6	1.01	9.00	5.00	1.00	5.00	MEK	940
Comp. 1-NS	TBAPF6	0.98	9.00	5.00	0.00	5.00	MEK	940
Comp. 2	TBABr	1.01	9.00	5.00	1.00	5.00	MEK	450
Comp. 2-NS	TBABr	1.01	9.00	5.00	0.00	5.00	MEK	470
Comp. 3	TBANO 3	1.02	9.00	5.00	1.00	5.00	MEK	620
Comp. 3-NS	TBANO 3	0.98	9.00	5.00	0.00	5.00	MEK	620

CAB 551-0.01 is a cellulose acetate butyrate product with a low hydroxyl content (1.5 %) that is commercially available from Eastman.

Tego Glide® 410 is a polyether modified polysiloxane surfactant that is commercially available from Evonik.

Foralyn® is an ester of hydrogenated rosin commercially available from Eastman, specifically Foralyn® 110.

The salts and solvents used were obtained from Sigma Aldrich and Alfa Aesar.

Figure 1 shows in the rows labelled 1-NS, 1, C1-NS and C1 pairs of images printed on HDPE substrates using invention ink 1 without the siloxane surfactant, invention ink 1 with the siloxane surfactant, comparative ink 1 without the siloxane surfactant, and comparative ink 1 with the siloxane surfactant, respectively. The left-hand column (labelled A) shows each printed image before application of 810 tape, and the right-hand column (labelled B) shows each printed image after removal of the 810 tape.

Comparison of images 1-NS B and 1 B shows that the presence of the siloxane surfactant in invention ink 1 significantly improved the adhesion of the printed image to the substrate.

Comparison of images C1-NS B and C1 B shows that the presence of the siloxane surfactant in comparative ink 1, on the other hand, significantly reduced the adhesion of the printed image to the substrate.

It will be noted that from a comparison of images 1-NS A and 1 A and C1-NS A and C1 A that the presence of the siloxane surfactant in the invention and comparative inks reduced the spreading of the droplets making up the printed images across the HDPE substrate. This effect appears to be independent of any effect on adhesion.

#### *Tape Removal Adhesion Test Results*

Tape removal adhesion tests as described above were carried out for each of the invention inks and comparative inks set out in Table 1 above by printing a printed image using each of the inks on substrates of each type (HDPE, LDPE and PP). Each of the printed substrates was then subjected to the tape removal adhesion test in triplicate, i.e. three printed images were tested on each type of substrate for each ink, and the average of the results calculated for each ink. The results are provided in Table 2 below.

Table 2 – Tape Removal Adhesion Test Results

Ink	Salt used	ISO TAPE (% Ink Removed)			810 TAPE (% Ink Removed)		
		HDPE	LDPE	PP	HDPE	LDPE	PP
1	KPF6	13	1	48	11	22	23
1-NS	KPF6	70	90	95	95	90	96
2	NaI	35	82	70	61	84	74
2-NS	NaI	86	30	86	90	94	95
3	KSCN	95	94	91	89	99	95
3-NS	KSCN	99	98	96	99	98	100
4	NaSCN	80	95	88	78	97	83
4-NS	NaSCN	98	100	93	98	100	99
Comp. 1	TBAPF6	89	100	100	95	100	100
Comp. 1-NS	TBAPF6	6	28	26	31	14	58
Comp. 2	TBABr				95	95	95
Comp. 2-NS	TBABr				5	5	5
Comp. 3	TBANO3				95	95	95
Comp. 3-NS	TBANO3				20	20	20

The tape removal adhesion test results show a clear improvement in adhesion for invention inks 1 to 4, which include the metal salts potassium hexafluorophosphate (KPF6), sodium iodide (NaI), potassium thiocyanate (KSCN) and sodium thiocyanate (NaSCN), respectively, when the siloxane surfactant is present. Conversely, a marked deterioration in adhesion is

seen for comparative inks 1 to 3, which include the non-metal salts tetrabutylammonium hexafluorophosphate (TBAPF6), tetrabutylammonium bromide (TBABr) and tetrabutylammonium nitrate (TBANO3), respectively, when the siloxane surfactant is present.

#### *Metal Conductivity Salt Concentration*

The effect of the concentration of the metal conductivity salt was studied.

A range of inks was prepared using the procedure set out above with varying amounts of the metal conductivity salt. The formulations of the inks are set out in Table 3 below.

Table 3 – Varying Salt Concentration Compositions

Ink	Salt used	Raw materials wt.%					Solvent <i>used to make up the formulation to 100wt.%</i>	Conductivity $\mu\text{S}/\text{cm}$
		Salt	CAB-551-0.01	Foralyn® 110	Tego Glide® 410	Pigment Dispersion 01		
5	KPF6	0.31	9.00	5.00	1.00	5.00	MEK	560
6	KPF6	0.49	9.00	5.00	1.00	5.00	MEK	810
1	KPF6	1.00	9.00	5.00	1.00	5.00	MEK	1326
7	KPF6	1.52	9.00	5.00	1.00	5.00	MEK	1860
8	KPF6	1.96	9.00	5.00	1.00	5.00	MEK	2200
9	NaI	0.47	9.00	5.00	1.00	5.00	MEK	800
2	NaI	0.89	9.00	5.00	1.00	5.00	MEK	908
10	NaI	1.55	9.00	5.00	1.00	5.00	MEK	2000
11	KSCN	0.54	9.00	5.00	1.00	5.00	MEK	1318
3	KSCN	1.01	9.00	5.00	1.00	5.00	MEK	1070
12	KSCN	1.53	9.00	5.00	1.00	5.00	MEK	2880

Tape removal adhesion tests as described above were carried out on each of the inks. The results of these tests are shown in Table 4 below.

Table 4 – Varying Salt Concentration Results

Ink	Salt used	ISO TAPE (% Ink Removed)			810 TAPE (% Ink Removed)		
		HDPE	LDPE	PP	HDPE	LDPE	PP
5	KPF6	27	38	22	14	57	39
6	KPF6	8	45	6	17	50	21
1	KPF6	13	1	48	11	22	23
7	KPF6	52	52	86	24	33	89
8	KPF6	44	18	82	28	50	84
9	Nal	88	81	93	70	87	89
2	Nal	35	82	70	61	84	74
10	Nal	95	92	99	80	95	88
11	KSCN	95	80	95	71	55	89
3	KSCN	96	94	91	89	99	95
12	KSCN	98	98	90	88	99	88

Good adhesion can generally be seen for the invention inks containing KPF6 or Nal, with the best adhesion results for the KPF6 series being seen for invention ink 1 and the best adhesion results for the Nal series being seen for invention ink 2.

In the KSCN series the best adhesion results are seen for invention ink 11.

#### *Surfactant Amount*

The effect of the amount of surfactant was studied.

A range of inks was prepared using the procedure set out above with varying amounts of the siloxane surfactant. The formulations of the inks are set out in Table 5 below.

Table 5– Varying Surfactant Amount Compositions

Ink	Salt used	Raw materials wt. %					Solvent <i>used to make up the formulation to 100wt. %</i>
		KPF6	CAB-551-0.01	Foralyn® 110	Tego Glide® 410	Pigment Dispersion 01	
13 - NS	KPF6	1.01	9.00	5.00	0.00	5.00	MEK
Comp. 14	KPF6	1.01	9.00	5.00	0.06	5.00	MEK
Comp. 15	KPF6	1.01	9.00	5.00	0.27	5.00	MEK
16	KPF6	1.01	9.00	5.00	0.52	5.00	MEK
17	KPF6	1.00	9.00	5.00	0.72	5.00	MEK
1	KPF6	1.00	9.00	5.00	1.02	5.00	MEK
18	KPF6	0.99	9.00	5.00	2.00	5.00	MEK

Tape removal adhesion tests as described above were carried out on each of the inks using ISO tape on the LDPE substrate only. The results of these tests are shown in Table 6 below.

Table 6 – Varying Surfactant Amount Results

Ink	Tego Glide® 410 wt%	(% Ink Removed)	
		ISO TAPE	810
		LDPE only	
13 - NS	0.00	84	95
Comp. 14	0.06	68	86
Comp. 15	0.27	60	56
16	0.52	40	23
17	0.72	31	20
1	1.02	10	26
18	2.00	13	11

Good adhesion is seen for invention inks 16, 17, 1 and 18, with the best adhesion results being seen for invention inks 1 and 18. Invention inks 16 and 17 can be seen to give similar adhesion results to invention ink 1 when tested using the 810 tape.

#### *Surfactant Type*

The effects of different surfactants were studied.

A range of inks was prepared using the procedure set out above with different surfactant types. The formulations of the inks are set out in Table 7 below.

Table 7 – Different Surfactant Compositions

Ink	Surfactant Used	Raw materials wt. %					Solvent <i>used to make up the formulation to 100wt. %</i>
		KPF6	CAB-551-0.01	Foralyn® 110	Surfactant	Pigment Dispersion 01	
Comp. 19	Tego® Wet 500	1.00	9.00	5.00	1.00	5.00	MEK
20	BYK® 333	1.00	9.00	5.00	1.00	5.00	MEK
1	Tego Glide® 410	1.00	9.00	5.00	1.00	5.00	MEK

BYK® 333 is a polyether modified polydimethylsiloxane surfactant available from BYK®.

Tego® Wet 500 is a non-ionic organic surfactant available from Evonik. Tego® Wet 500 is silicone free.

Tape removal adhesion tests as described above were carried out on each of the inks. The results of these tests are shown in Table 8 below.

Table 8 – Different Surfactant Results

Ink	Surfactant Used	ISO TAPE (% Ink Removed)			810 TAPE (% Ink Removed)		
		HDPE	LDPE	PP	HDPE	LDPE	PP
Comp. 19	Tego® Wet 500	67	48	93	88	83	93
20	BYK® 333	23	7	38	20	13	69
1	Tego Glide® 410	13	1	49	11	22	23

Good adhesion is seen for invention inks 20 and 1, particularly on HDPE and LDPE substrates. The adhesion of comparative ink 19, which contains a surfactant that is not a siloxane surfactant, is disappointing.

#### *Different Colourants*

The effects of different colourants were studied.

A range of inks was prepared using the procedure set out above with different colourants. The formulations of the inks are set out Table 9 below.

Table 9 – Different Colourant Compositions

Ink	Colourant Used	Salt Used	Raw materials wt.%					Solvent used to make up the formulation to 100wt.%	Conductivity $\mu\text{S}/\text{cm}$
			Salt	CAB-551-0.01	Foralyn® 110	Tego Glide® 410	Colourant		
Comp. 4	Orasol® 855	TBAP F6	0.98	9.00	5.00	1.00	1.50	MEK	977
21*	Orasol® 855	KPF6	0.96	9.00	5.00	1.00	1.50	MEK	1620
Comp. 5	Solvaperm® blue 2B	TBAP F6	0.98	9.00	5.00	1.00	1.50	MEK	1010
22*	Solvaperm® blue 2B	KPF6	1.00	9.00	5.00	1.00	1.50	MEK	1475

\* indicates a reference example.

Solvaperm® Blue 2B is a solvent blue 104 dye that is commercially available from Clariant.

Orasol® 855 is a solvent blue 70 dye that is commercially available from BASF® SE.

Tape removal adhesion tests were carried out on each of the inks, but instead of using the Matlab® software to compare before and after photographs, a simple visual inspection was carried out and the adhesion graded in accordance with the criteria set out in Table 10 below. The resulting gradings are set out in Table 11 below.

Table 10 – Grading Criteria for Adhesion

Grading System for Adhesion	
Excellent	No ink removed
Good	Some dots removed, very easy to read the code
Moderate	Code partially removed, possible to read the code
Poor	Most dots removed, not possible to read
Very Poor	Code completely removed

Table 11 – Different Colourant Results

Ink	Colourant Used	Salt Used	ISO TAPE			810 TAPE		
			HDPE	LDPE	PP	HDPE	LDPE	PP
Comp. 4	Orasol® 855	TBAPF6	Poor	Poor	Poor	Poor	Very Poor	Poor
21*	Orasol® 855	KPF6	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Comp. 5	Solvaperm® blue 2B	TBAPF6	very poor	very poor	very poor	very poor	very poor	very poor
22*	Solvaperm® blue 2B	KPF6	Good	Good	Moderate	Good	Good	Good

\*\* indicates a reference example.

The tape removal adhesion test generally shows at least good adhesion for invention inks 21 and 22, which use colourants in the form of solvent dyes. The poor adhesion of comparative inks using the same colourants but a non-metal conductivity salt is striking.

#### *Different Solvents*

The effects of different solvents, metal conductivity salts, and pigment dispersions were studied.

A range of inks was prepared using the procedure set out above with different solvents, metal conductivity salts and pigment dispersions. The adhesion promoters Tego® Variplus CA and Tytan® AP 100 were also included. The formulations of the inks are set out in Table 12 below.

Table 12 – Different Solvents, Metal Conductivity Salts and Pigment Dispersions Compositions

Ink	Salt Used	Raw materials wt.%							Conductivity $\mu\text{S}/\text{cm}$	Solvent used to make up the formulation to 100wt. %
		Salt	CAB - 551-0.01	Foralyn® 110	Tego Glide® 410	Pigment Dispersi on 02	Tego® Variplus CA	Tytan® AP100		
23	KI	1.52	5.00	2.00	1.00	5.00	10.00	3.00	730	
23-NS	KI	1.52	5.00	2.00	0.00	5.00	10.00	3.00	760	
24	LiNO <sub>3</sub>	2.06	5.00	2.00	1.00	5.00	10.00	3.00	1270	
24-NS	LiNO <sub>3</sub>	2.06	5.00	2.00	0.00	5.00	10.00	3.00	1320	

Tego® Variplus CA is a ketone condensation resin available from Evonik.

Tytan® AP 100 is a titanium phosphate complex from Borica Company Ltd.

Tape removal adhesion tests as described above were carried out on each of the inks using the Matlab® software. The results of these tests are shown in Table 13 below.

Table 13 – Different Solvents, Metal Conductivity Salts and Pigment Dispersions Results

Ink	Salt Used	ISO TAPE			810 TAPE		
		HDPE	LDPE	PP	HDPE	LDPE	PP
23	KI	17	15	20	14	10	29
23-NS	KI	20	42	61	32	19	67
24	LiNO <sub>3</sub>	14	22	2	26	20	23
24-NS	LiNO <sub>3</sub>	39	21	53	44	44	64

Good adhesion is seen for invention inks 23 and 24, which both use a liquid carrier in the form of a mixture of the organic solvents ethanol and ethyl acetate, and use a metal conductivity salt in the form of potassium iodide and lithium nitrate, respectively.

12 05 23



**Claims**

1. An ink composition comprising a liquid carrier, a colourant, a siloxane surfactant and a metal conductivity salt, wherein the siloxane surfactant is present in an amount of at least 0.3% by weight of the ink composition and the siloxane surfactant comprises a polyether modified siloxane surfactant, ~~and wherein the metal conductivity salt is selected from the group consisting of lithium nitrate, potassium hexafluorophosphate, potassium thiocyanate, sodium thiocyanate, sodium iodide and potassium iodide, and wherein the colourant comprises a carbon black.~~

2. The ink composition of claim 1, wherein the liquid carrier comprises at least one organic solvent.

3. The ink composition of claim 2, wherein the at least one organic solvent comprises at least one of methyl ethyl ketone, acetone and ethanol.

4. The ink composition of claim 2 or 3, wherein the at least one organic solvent comprises a mixture of ethanol and ethyl acetate, or a mixture of ethanol and methyl ethyl ketone, or a mixture of acetone, methyl acetate and ethyl acetate.

5. The ink composition of any preceding claim, wherein the ink composition in the absence of the metal conductivity salt has a conductivity of less than 500  $\mu\text{S}/\text{cm}$ .

~~6. The ink composition of any preceding claim, wherein the colourant comprises a carbon black.~~

~~6~~7. The ink composition of ~~any preceding claim~~claim-6, wherein the colourant comprises a dispersion of the carbon black.

~~7~~8. The ink composition of any preceding claim, wherein the metal conductivity salt comprises at least one of potassium hexafluorophosphate and potassium iodide.

~~8~~9. The ink composition of any preceding claim, wherein the metal conductivity salt is present in an amount of 0.3 to 4.0 % by weight of the ink composition.

~~9~~10. An ink cartridge containing an ink composition according to any of claims 1 to ~~9~~9.

~~10~~11. A printing method comprising the steps of depositing an ink composition according to any of claims 1 to ~~9~~9 onto a substrate, and permitting at least partial evaporation of at least a component of the liquid carrier.

1142. The printing method of claim 1044, wherein the step of depositing the ink composition onto the substrate comprises ejecting droplets of the ink composition from an inkjet print head onto the substrate.

1240. An article marked with a printed deposit using the method of claim 1044 or 1142.

12 05 23