

FABRIC 2 PLY

SUPERFELX: 820

www.stretch.com

FABRIC SPECS				
PROPERTIES	VALUE	MIN/MAX	UNIT	TEST METHOD
FABRIC WIDTH	1.5 M			
FABRIC WEIGHT	820 GSM			
Colour fastness to light (min) Blue Scale	6	min	Grey Scale	ASTM D 2263 Method C
Colour fastness to wet and dry Rubbing (Grey Scale)	4	min		
Tensile strenght WMD	950	min	n/50mm	Bs3424 P4
Tensile strenght AMD	750	min	n/50mm	Bs3424 P4
Elongation under constant load WMD	20		%	10kg/10min
Elongation under constant load AMD	30		%	10kg/10min
Bursting resistance	20	min	kg/Sqr cm	Mullen
Resistance to flexions	ok		No Disintergration	Bs 3424.83 P22
Water column	2m		No drops	ASTM D 751
FIRE RATING: PASSED				M2, B1, CSFM, BS7837



white



stone



sand/chino



grey



Black